# Fusor® 121/124 Flexible Foam (Super Fast)

#### Technical Data Sheet

Fusor® 121/124 flexible foam is a two-component, urethanebased foam used for sound deadening and sealing/filling of door skins to crash bar, hood panel to supports, trunk panel to supports and gas tank filler area.

#### Features and Benefits:

**Versatile** – expands to ten times its size; retains memory with no shrinkage.

**Excellent Appearance** – matches OEM sound deadening

Environmentally Resistant - will not absorb moisture or cause corrosion.

#### Application:

Prepare - Remove any necessary panels and use a drop cloth to protect the surrounding area against accidental drippage.

Apply - Load cartridge into a manual dispensing gun and remove the end cap(s) from cartridge packaging. Note there are two different cartridge packages in distribution. The original snip-off package which uses two supplied plugs to reseal when complete and the new snap-off package which reuses the snap-off cap as the plugging mechanism.

Prepare foam for application by gently squeezing out a small amount of material to ensure that material freely flows from both sides of the cartridge. Attach mixing tip.

Note: Due to the thin viscosity of the material, a pneumatic gun is not recommended.

Apply a bead of foam between the vibrating panels. Avoid dispensing material too quickly. Foam will expand approximately 10 times its original volume to fill voids or eliminate vibration.

When sealing pillars or posts, apply a sufficient amount of foam; approximately 1/3 of a cartridge may be needed depending on size and configuration of void.

Remove the mixing tip immediately after usage and install supplied cartridge plugs/cap to avoid pressure build-up. With newer cartridge packaging, reinstall cap by aligning the circle and square on the cap with the same symbols on the cartridge head and snap down.

Note: Various applications, cleaners/solvents and coatings may not be compatible with this product and should be tested by the user before proceeding with intended repair procedure.

Finish – If desired, foam can be painted in 10 minutes.

For more application information, refer to www.lord.com/ fusor for standard operating procedures or application training videos.

Typical Properties*	
Appearance	Black Foam
Base Chemistry	Urethane
Work Time	10 seconds @ 70°F (21°C)
Full Expansion	3 minutes @ 70°F (21°C)
Paint Time	10 minutes @ 70°F (21°C)
Full Cure	1 hour @ 70°F (21°C)

<sup>\*</sup>Data is typical and not to be used for specification purposes.





#### **Technical Tips**

 When applying Fusor 121/124 flexible foam to a vertical panel, dispense the material to the end of the tip. Allow the material to start foaming, then slowly dispense into the appropriate area. This will keep the material from running down the panel.

## Shelf Life/Storage

Shelf life is 24 months from date of manufacture when stored at 75°F (24°C) in original, unopened container.

### **Cautionary Information:**

Before using this or any Parker LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

#### Fusor® Repair Products Lifetime Guarantee\*

LORD Assembly & Protection Solutions Division of Parker-Hannifin Corporation ("Parker LORD") guarantees to the user that Fusor® Repair Products (adhesives, primers, seam sealers and foams only), when used in strict accordance with Parker LORD application and use instructions, will provide a durable repair for the life of the vehicle per the product's technical data sheet. The user is solely responsible for determining the Fusor product and application method for the repair. Application and product guidance can be found on

THIS EXPRESS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, BY OPERATION OF LAW OR OTHERWISE. INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Parker LORD shall not be liable under any circumstance for any liability, loss, damage or expense directly or indirectly arising from the application and use of Fusor Products sold hereunder or from any other cause. Parker LORD shall not be liable under any circumstances for consequential, indirect or special damages. PARKER LORD'S LIABILITY FOR BREACH OF WARRANTY HEREUNDER IS IN ALL INSTANCES LIMITED SOLELY AND EXCLUSIVELY TO THE REASONABLE COSTS OF REPAIR AND/OR REPLACEMENT OF THE BONDED COMPONENTS OF THE VEHICLE.

This guarantee shall only apply to the above referenced Fusor products sold by Parker LORD on or after January 1, 2001.

Fusor Metal Bonding Adhesives shall only be used for the adhesive-only bonding (no welds or rivets) of metal to metal assemblies (steel or aluminum) in full or partial panel replacements of door skins, roof skins, quarter panels, rear body panels and other outer body sheet metal where approved by the vehicle manufacturer.

Fusor products shall not be used for adhesive-only bonding of any structural component unless specifically recommended by the vehicle manufacturer. Structural panels must be replaced in strict compliance with vehicle manufacturer guidelines. If in doubt as to what is a structural component or the proper installation method, contact the vehicle manufacturer. Further, any Fusor products used in marine composite repair, such as with personal water craft and the like, shall be limited to repairs above the water line.

If you have any questions or need to receive proper use instructions, contact the Parker LORD Customer Support Center at +1 800 234 Fusor (3876) or visit Fusor.com.

To comply with the requirements of the Fusor Repair Products Lifetime Guarantee, attach a copy of this completed page to the repair record, and retain with your files:

Vehicle Make/Model:	
Vehicle Identification Number:	
Fusor Product(s) Used for Repair	

Lot Number(s) on Cartridge(s) Used for Repair:

\*This guarantee is void if product is used after the date printed on the cartridge label. Parker LORD Terms and Conditions of Sale shall apply to all sales of Fusor products.





Instructions contained in this document need to be followed to qualify for the LORD Fusor Lifetime Guarantee. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Cente

Information provided herein is based upon tests believed to be reliable. In as much as Parker LORD has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker LORD does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use

WARNING - USER RESPONSIBILITY, FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems

©2020 Parker Hannifin - All Rights Reserved

Information and specifications subject to change without notice and without liability therefor. Trademarks used herein are the property of their respective owners

DS6210

03/20 Rev 0

Parker LORD **Engineered Materials Group** 

> 111 LORD Drive Cary, NC 27511-7923

USA

phone +1 877 ASK LORD (275 5673)

www.lord.com



